



Bio-Cellulose Window Patching film (TDS)

Property	Units		Test Conditions	Test Method	Result	Result
Thickness	Micron		/	Keyful Test	150	250
Yield	m ² /kg		/	Keyful Test	4.6	2.76
	g/m ²		/		217	362.3
Width	mm		/	Keyful Test	100MM-880MM	100MM-880MM
Length	m		/	Keyful Test	500M	500M
Gloss	%		60°	ASTM D523, BS 2782 520A	146	142
Haze	%		/	ASTM D1003, BS 2782 521A	1.7	2.3
Tensile strength	MN/m ²	MD	/	ASTM D 882	108	108
		TD			82	82
Elongation at break	%	MD	/	ASTM D 882	25	25
		TD			50	50
Softening temperature	°c		/	/	127	127
Glass transition temperature	°c		/	/	92	92

Remark: The data above is reference values, not standard values.

Add: F6-05C, 6th Floor, Building F, Cultural Creative Park, Shatou Street, Futian District, Shenzhen, China.

Tel: +86 0755 8291 0699

E-Mail: melissa@kfnmsz.com

Web Sites: www.keyfulgroup.com