



Bio-Cellulose tapes film (TDS)

Property	Units	Test Method	Result
Basic Film Thickness	Micron	Keyful Test	29
Glue Thickness	Micron	Keyful Test	24
Yield	m ² /kg	Keyful Test	24.2
	g/m ²		41.4
Width	mm	Keyful Test	20MM-860MM
Length	m	Keyful Test	20m-200M
Viscosity	N	Keyful Test	9.9
Peeling Strength	/	Keyful Test	9N/25mm
Tensile strength	N/15MM	MD	76
		TD	42
Elongation at break	%	MD	20
		TD	36
Antistatic value	/	Keyful Test	4.9x10⁻¹³
Surface tension	Dyne	/	42

Remark: The data above is reference values, not standard values.

Add: F6-05C, 6th Floor, Building F, Cultural Creative Park, Shatou Street, Futian District, Shenzhen, China.

Tel: +86 0755 8291 0699

E-Mail: melissa@kfnmsz.com

Web Sites: www.keyfulgroup.com